# Performance Expectations for Threaded Inserts in Plastic Assemblies

# WHITE PAPER

SPIROL

by Tara Meinck - Product Manager SPIROL International Corporation



The use of **Threaded Inserts** in plastic assemblies allow designers to replace machined and cast metal components with plastic to achieve significant cost and weight savings without any loss of joint strength.

Some of the most common questions asked by designers are "What kind of performance can I expect from this type of Insert?" – and – "Will this Insert meet the performance specification on my drawing?" While on the surface these questions seem relatively easy to answer, it's actually nearly impossible to answer with a simple "yes" or "no;" but rather "it depends."

Insert performance, or resistance to rotational torque and tensile loading (also known as pull-out), is only partially influenced by the Insert itself. Other factors that impact Insert performance include:

- · Plastic material and filler composition,
- Design and quality of the plastic components including hole consistency,
- Installation process and resultant quality, and
- Alignment of the mating component and how it supports the installed Insert.


There are so many different combinations of Insert materials, plastic types, and assembly configurations (local to the joint) that without understanding these factors, it is impossible to determine what performance could be achieved in a specific application. Additionally, as much as 75% of the Insert's performance is a direct result of how well it was installed.

In order to establish a true benchmark for an application, it is imperative to assemble and test the bolted joint under the application's production environment. Since questions surrounding performance often arise earlier in the design process, it is important to consider which of the previously listed factors may be easily adjusted compared to those with a more significant impact if modified. An Insert can be recommended to meet a specific application's requirements in the design stage, and/or modifications can be proposed to an existing assembly to optimize performance based on prior experience and extensive performance data. In some cases,

it is preferred to test the Insert in the application to determine the installation criteria that will yield the best performance. Ultimately, acceptance of any Threaded Insert is subject to testing and evaluation to confirm performance in the actual application.

Once a benchmark has been established and the application moves into production, it is imperative to remember that variation to any of the aforementioned factors may affect the Threaded Insert's ability to resist rotational torque and pull out. Limiting the number of suppliers involved with an assembly can also minimize variables that affect performance. Therefore, if possible, purchase both the Threaded Inserts and Installation Equipment from the same supplier.

Many Insert manufacturers provide performance data in their product catalog. This data should be used solely as a comparative guide for Insert types and sizes. This performance data should not be used to compare across manufacturers since testing methods and materials are not consistent, nor should it be used to estimate a performance benchmark.



Threaded Insert performance testing methods: (left) Tensile (Pull-out) Strength and (right) Rotational Torque

### **Conclusion:**

Given the variety of plastic materials and fillers and the complexity of component design, it is impossible to provide Insert performance data which can be applied to specific applications. It is recommended that designers partner with Application Engineering experts who specialize in Threaded Inserts for Plastics as early as possible in the design stage to determine the most appropriate Insert for their assembly. Final approval of the Threaded Insert should always be based on testing and approval in the actual application.



## Innovative fastening solutions. Lower assembly costs.



**Coiled Spring Pins** 



Alignment Dowels / **Bushings** 



**Threaded Inserts** for Plastics



**Precision Shims & Thin Metal Stampings** 



**Pin Installation Technology** 



**Slotted Spring Pins** 



Spacers & Rolled **Tubular Components** 



**Railroad Nuts** 

**Precision Washers** 



Parts Feeding Technology

**Disc Springs** 



**Compression Limiter** Installation Technology

Please refer to www.SPIROL.ca for current specifications and standard product offerings.

**Insert Installation** 

Technology

SPIROL offers complimentary Application Engineering support! We will assist on new designs as well as help resolve issues, and recommend cost savings on existing designs. Let us help by visiting Application Engineering Services on SPIROL.ca.

© 2022 SPIROL International Corporation 08/22



Solid Pins



Compression Limiters



**Technical Centres** 

#### Americas **SPIROL** Canada

3103 St. Etienne Boulevard Windsor, Ontario N8W 5B1 Canada Tel. +1 519 974 3334 Fax. +1 519 974 6550

**SPIROL** International Corporation

30 Rock Avenue Danielson, Connecticut 06239 U.S.A. Tel. +1 860 774 8571 Fax +1 860 774 2048

**SPIROL Shim Division** 321 Remington Road Stow, Ohio 44224 U.S.A. Tel. +1 330 920 3655 Fax. +1 330 920 3659

#### **SPIROL Mexico**

Avenida Avante #250 Parque Industrial Avante Apodaca Apodaca, N.L. 66607 Mexico Tel. +52 81 8385 4390 Fax. +52 81 8385 4391

SPIROL Brazil Rua Mafalda Barnabé Soliane, 134 Comercial Vitória Martini, Distrito Industrial CEP 13347-610, Indaiatuba, SP, Brazil Tel. +55 19 3936 2701 Fax. +55 19 3936 7121

Europe SPIROL United Kingdom

17 Princewood Road Corby, Northants NN17 4ET United Kingdom Tel: +44 (0) 1536 444800 Fax: +44 (0) 1536 203415

**SPIROL France** Cité de l'Automobile ZAC Croix Blandin 18 Rue Léna Bernstein 51100 Reims, France Tel: +33 (0) 3 26 36 31 42 Fax: +33 (0) 3 26 09 19 76

**SPIROL Germany** Ottostr. 4 80333 Munich, Germany Tel: +49 (0) 89 4 111 905 71 Fax: +49 (0) 89 4 111 905 72

**SPIROL Spain** Plantes 3 i 4 Gran Via de Carles III 84 08028, Barcelona, Spain Tel/Fax: +34 932 71 64 28

**SPIROL Czech Republic** Evropská 2588 / 33a 160 00 Prague 6-Dejvice Czech Republic Tel: +420 226 218 935

SPIROL Poland ul. Solec 38 lok. 10 00-394, Warsaw, Poland Tel. +48 510 039 345

Asia Pacific

**SPIROL Asia Headquarters** 1st Floor, Building 22, Plot D9, District D No. 122 HeDan Road Wai Gao Qiao Free Trade Zone Shanghai, China 200131 Tel: +86 (0) 21 5046-1451 Fax: +86 (0) 21 5046-1540

**SPIROL Korea** 16th Floor, 396 Seocho-daero, Seocho-gu, Seoul, 06619, South Korea Tel: +82 (0) 10 9429 1451

e-mail: info-ca@spirol.com

